



NOTES:

- 1.ASSEMBLY METHOD:INSERT 2 AND 3 INTO THE 1 THEN HEATING 7MINUTES AT 82°c.
- 2.SUMITUBE C:FLEXIBLE COMMERCIAL GRAD POLYOLEFIN.
 OPERATION TEMPERATURE:-55°c TO 100°c.
 TENSILE STRENGTH(kg/mm²):1.0 min.
 ELONGATION(%):200 min.
 SPECIFIC GRAVITY:0.94
 WATER ABSORPTION(%):0.3 max.
 LONGITUDINAL SHRINKAG(%):15 max.
 DIELECTRIC STRENGTH(kV):AC 2.5 min.
 VOLUME RESISTIVITY(ohm-cm):10¹⁴min.

PART NO.	A
FIBER-232-40	40 mm
FIBER-232-50	50 mm
FIBER-232-60	60 mm

3	PIN	1	SUS303
2	SUMITUBE C	1	POLYOLEFIN
1	SUMITUBE C	1	POLYOLEFIN
NO.	DESCRIPTION	Q'TY	MATERIAL



圖名 NAME: FIBER-232-XX

圖號 DVG NO:

單位 UNIT	MM	一般公差 .X _____ .XX _____ .XXX _____ ANGLES _____	繪圖 DRAW. BY	AXL
比例 SCALE	NONE		校對 CHECKED	
圖號 SHEET	1/1		審核 APPVL. BY	

[A]	ISSUED	8/19/03'	AXL	
REV	DESCRIPTION	DATE	NAME	ECN NO.